



TC-5389

**ELECTRICAL RESEARCH AND DEVELOPMENT ASSOCIATION**

(Accredited by the National Accreditation Board for Testing and Calibration Laboratories, Govt. of India)

ERDA Road, Makarpura Industrial Estate, Vadodara-390 010, India.

EPABX : +91 (0265) 2642942, 2642964, 2642377, 3043128 / 29 / 30 / 31 / 33

Fax : +91 (0265) 2638382



E-mail : erda@erda.org

Web : http://www.erda.org



RP-2425-037791

**TEST REPORT****ULR No.: TC538925000005614F****SHEET 01 OF 03**

<b>NAME &amp; ADDRESS OF CUSTOMER:</b>  <b>M/s. Paragon Electro Switchgear Pvt. Ltd.</b> <b>K-3, M.I.D.C., Ambad,</b> <b>Nashik – 422 010.</b> <b>Maharashtra.</b> <b>INDIA</b>	<b>REPORT NO. : RP-2425-037791</b> <b>DATE OF ISSUE: 05-03-2025</b>	
	<b>CUSTOMER REF. NO.:</b> Letter <b>DATED:</b> Nil	
	<b>DATE OF SAMPLE RECEIPT</b>	<b>DATE OF TESTING</b>
	17-12-2024	04-03-2025 & 05-03-2025
<b>SAMPLE DESCRIPTION:</b> (As provided by customer)  <b>Compression type tubular terminal ends (Aluminium lug) [5 Nos.]</b> <b>Designation: CAA-300</b> <b>PESALS-300 (300 sqmm E-16.2 Aluminium Lug)</b>	<b>SAMPLE IDENTIFICATION:</b>  <b>Embossed on the sample:</b> "Pessrl-300-16"  <b>ERDA Sample Code No.:</b> ERDA-00610835	
<b>TEST DETAILS:</b> 1] Visual examination 2] Dimensional check up 3] Flattening test 4] Electrical conductivity test [% IACS]	<b>TEST SPECIFICATION:</b>  <b>For Test Procedure and Requirement:</b> IS 8309 : 1993 with 1 Amendment	
<b>REMARKS:</b> 1] Out of five samples, one sample was randomly selected for testing. 2] Sample conforms to the requirement of all above mentioned tests. 3] Photograph of samples has been attached. [Refer SHEET 03 OF 03]		
 <b>CHECKED BY</b>	 <b>(Mr. Anil Suthar)</b> <b>APPROVED BY</b>	

Note:

1. This report relates only to the particular sample received for testing in good condition at ERDA Vadodara.
2. This report cannot be reproduced in part under any circumstances.
3. Publication of this report requires prior permission in writing from Director, ERDA.
4. This report shall not be used for any purpose such as PR brochures, propaganda, advertisement and/or legal proceedings, unless for the granted purpose.
5. Only the tests asked for by the customer have been carried out.
6. Particulars of manufacturer/supplier, given in this report are based on information supplied by the customer, along with the test request/sample. ERDA does not assume any responsibility for the correctness of the information for above mentioned Sample Under Test (SUT). ERDA will not be responsible for any changes in SUT made after the test. This test report is given as per instrument status while testing.
7. In case of any dispute, Vadodara will be the exclusive jurisdiction & shall be construed as where the cause has arisen.

**Caution:** ERDA is not responsible for the authenticity of photocopied or reproduced test reports.

ERDA provides support to customers for verification of the authenticity of test reports issued by ERDA within 10 years of date of issue of report.

TC 3763573



TC-5389

**ELECTRICAL RESEARCH AND DEVELOPMENT ASSOCIATION**

(Accredited by the National Accreditation Board for Testing and Calibration Laboratories, Govt. of India)

ERDA Road, Makarpura Industrial Estate, Vadodara-390 010, India.

EPABX : +91 (0265) 2642942, 2642964, 2642377, 3043128 / 29 / 30 / 31 / 33

Fax : +91 (0265) 2638382

E-mail : erda@erda.org

Web : http://www.erda.org

**ULR No.: TC538925000005614F**

Discipline: Electrical Testing

Group: Transmission line equipment and accessories

**TEST REPORT No.: RP-2425-037791****DATE OF ISSUE: 05-03-2025****SHEET 02 OF 03**

Sr. No.	Particular of Tests & Cl. No.	Requirement as per specification	Obtained Value/ Observation	Remarks
1.	<b>Visual examination</b> [Cl. No. 8.1 of IS 8309]	Sample shall be examined for freedom from flaws, rust, crevices, cracks and other defects harmful for the joint.	Sample found free from flaws, rust, crevices, cracks and other defects harmful for the joint.	Conforms
2.	<b>Dimensional check up</b> [Cl. No. 8.1 & Table 1 of IS 8309]	Sample shall conform to Designation CAA-300 of Table 1 of IS 8309	Conforms to Designation CAA-300 of Table 1 of IS 8309	Conforms
3.	<b>Flattening test</b> [Cl. No. 8.2 of IS 8309]	Apply gradually increasing load until the internal surfaces are in contact over at least half of the internal width of flattened test piece. There shall be no crack observed.	No crack was observed	Conforms
4.	<b>Electrical conductivity test [% IACS]</b> [Cl. No. 8.3 of IS 8309]	60.0 % IACS (Min.)	62.8 % IACS*	Conforms

**Note:** '\*' Obtained value is an average of five readings.**CHECKED BY****TC 3763431**



TC-5389

## ELECTRICAL RESEARCH AND DEVELOPMENT ASSOCIATION

(Accredited by the National Accreditation Board for Testing and Calibration Laboratories, Govt. of India)

ERDA Road, Makarpura Industrial Estate, Vadodara-390 010, India.

EPABX : +91 (0265) 2642942, 2642964, 2642377, 3043128 / 29 / 30 / 31 / 33

Fax : +91 (0265) 2638382


E-mail : erda@erda.org

Web : http://www.erda.org



ULR No.: TC538925000005614F

TEST REPORT No.: RP-2425-037791 DATE OF ISSUE: 05-03-2025 SHEET 03 OF 03



Photograph of samples

CHECKED BY



\*\*\*\*\* End of Test Report \*\*\*\*\*

TC 3763432